

## Roundbelts

### PU70A twisted round belts sky blue smooth




approx. 76° Shore A

Recommended pretension

8...10 %

Order No.	Diameter Ø		Recommended Min. pulley Ø		Fmax/belt (Standard)	
	mm	inch	mm	inch	kg	lbs
FBXH3X250LG	5,0	1/5	40	1,6	2,5	5,5
FBXH3X710LG						

Available standard lengths of 250...710 mm



Coeff. of friction  $\mu$ : Steel: approx. 0,75 | FDA/EC/USDA compliant (Limited suitability EC)

### Symbols

Antistatic profile with outstanding mechanical properties.	Profile with exceptional low-temperature flexibility down to -30°C.	Patented material formulation „PLUS“ for lower product elongation.	Very good UV resistance.	Profiles with FDA/EC conformity for direct contact with food.	Metal and X-ray detectable profiles for maximum food safety.	Hydrolysis resistance (HY). Suitable for humid environments.	Microbe-resistant materials do not provide a breeding ground for microorganisms	Belt made of 2 components enables combination of hardness and features.

## Roundbelts

### PU75A **plus** twisted round belts orange smooth (matt)



approx. 80° Shore A

Recommended pretension 6...8 %










Order No.	Diameter $\varnothing$		Recommended Min. pulley $\varnothing$		Fmax/belt (Standard)	
	mm	inch	mm	inch	kg	lbs
FBX13X2500G FBX13X4500G	5,0	1/5	40	1,6	3,8	8,4

Available standard lengths of 250...710 mm



Coeff. of friction  $\mu$ : Steel: approx. 0,70

### Symbols

								
Antistatic profile with outstanding mechanical properties.	Profile with exceptional low-temperature flexibility down to -30°C.	Patented material formulation „PLUS“ for lower product elongation.	Very good UV resistance.	Profiles with FDA/EC conformity for direct contact with food.	Metal and X-ray detectable profiles for maximum food safety.	Hydrolysis resistance (HY). Suitable for humid environments.	Microbe-resistant materials do not provide a breeding ground for micro-organisms	Belt made of 2 components enables combination of hardness and features.